

## Trial Report

**Product** : **Metaform W550EP**  
**Customer** : S.P. Automotive Product Co., Ltd.  
**Application Details** : Forming  
**Part** : Automotive Part  
**Raw Material** : TSUS439 1.2 mm.



1. Spray on metal sheet (Dilute 20%)
2. Forming machine
3. In store 2 weeks.

### Result

Fail : Because has yellow oil on part is same rust.

